

## StoneLike (UV postcure)

### Features:

- Complex design models
- Extremely robust design models

Properties	Test Method	SI Unity	
<b>General Properties</b>			
Density (20° C)		g/cc	1,37
Colour			LIGHTGRAY
<b>Thermal Properties</b>			
HDT	D790M	°C	60-65
<b>Mechanical Properties</b>			
Tensile Strength	D638M	Mpa	47
Elongation at break	D638M	%	2,3
Flexural Modulus	D790M	Mpa	3500
Hardness		Shore D	93
<b>Production Properties</b>			
Layer thickness		mm	0.10-0,15
<b>Electrical Properties</b>			
Electric Strength	IEC 60243-1	kV/mm	28,7