

| | p.fisiche | trazione | | | flessione | | rottura | durezza | calore | | | acqua | | | |
|-----------------------------------|--|----------------------------|------------------------------|--------------------------|------------------------------|--------------------------|---------------------------------|-------------------------|------------|------------------------------|------------------------------|----------------------|---------------------|-------|-----------|
| MATERIALI MONOCOMPONENTE | | | | | | | | | | | | | | | |
| | RIGIDI | | carico a rottura oy (Mpa) | all. a rottura %e (%) | modulo flex. (Gpa) | res.Flex. (Mpa) | res.impatto Izod KIC (J / m) | Shore D | Rockwell M | T. Distors. @0,45Mpa (°C) | T. Distors. @1,82Mpa (°C) | Rammollin Tg (°C) | assorbimento (%) | | |
| | densità p (g / cm3) | modulo elastico E (Gpa) | | | | | | | | | | | | D-792 | D-638-04 |
| OPACHI | VeroWhitePlus | | 2,0-3,0 | 50-65 | 10-25 | 2,2-3,2 | 75-110 | 20-30 | - | 45-50 | - | - | 1,1-1,5 | | |
| | VeroWhitePlus FullCure 835 | | 1,17-1,18 | 2,2-2,7 | 57-60 | 12-16 | 2,3-3,2 | 80-110 | 20-30 | 83-86 | 73-76 | 46-49 | 45-50 | 52-54 | 1,25-1,4 |
| | VeroBlack FullCure 870 | | 1,17-1,18 | 2,2-2,7 | 57-60 | 12-16 | 2,3-3,2 | 80-110 | 20-30 | 83-86 | 73-76 | 46-49 | 45-50 | 52-54 | 1,25-1,4 |
| | VeroGray FullCure 850 | | 1,17-1,18 | 2,2-2,7 | 57-60 | 12-16 | 2,3-3,2 | 80-110 | 20-30 | 83-86 | 73-76 | 46-49 | 45-50 | 52-54 | 1,25-1,4 |
| | VeroBlue FullCure 840 | | 1,18-1,19 | 2,0-3,0 | 50-60 | 15-25 | 1,9-2,5 | 60-70 | 20-30 | 83-86 | 73-76 | 46-49 | 45-50 | 48-50 | 1,5-2,2 |
| HT | RGD525 High Temperature Material | | 0,97-0,98 | 3,2-3,5 | 70-80 | 10-15 | 3,1-3,5 | 110-130 | 14-16 | 87-88 | 78-83 | 63-67 | 55-57 | 62-65 | 1,2-1,4 |
| | RGD525 High T. Material CURED | | 0,97-0,98 | 3,2-3,5 | 70-80 | 10-15 | 3,1-3,5 | 110-130 | 14-16 | 87-88 | 78-83 | 63-67 | 55-57 | 62-65 | 1,2-1,4 |
| | ABS-like Material | | - | 2,6-2,8 | 50-60 | 25-40 | 1,7-2,1 | 65-70 | 65-75 | - | - | 58-68 | - | - | - |
| | ABS-like Material CURED | | - | 2,6-2,8 | 50-60 | 25-40 | 1,7-2,1 | 65-70 | 65-75 | - | - | 58-68 | - | - | - |
| | FullCure 720 | | 1,18-1,19 | 2,0-3,0 | 50-65 | 15-25 | 2,7-3,3 | 80-220 | 20-30 | 83-86 | 73-76 | 45-50 | 45-50 | 48-50 | 1,5-2,2 |
| PPI | VeroClear Material | | - | 2,0-2,7 | 55-62 | 10-20 | 2,1-2,6 | 75-90 | 20-30 | - | - | 48-51 | - | - | 1,38-1,42 |
| | VeroClear FullCure 810 | | 1,04-1,05 | 2,0-3,0 | 50-65 | 10-25 | 2,2-3,2 | 75-110 | 20-30 | 83-86 | 73-76 | 45-50 | 45-50 | 52-54 | 1,1-1,5 |
| | DurusWhite FullCure 430 | | 1,15-1,17 | 1,0-1,2 | 20-30 | 40-50 | 1,2-1,6 | 30-40 | 40-50 | 74-78 | - | 37-42 | 32-34 | 35-37 | 1,5-1,9 |
| GOMME | SIMILGOMMA | | densità p (g / cm3) | | carico a rottura oy (Mpa) | all. a rottura %e (%) | | res.Strappo (N / mm) | Shore A | | | | | | |
| | | | D-792 | | D-412 | D-412 | | D-624 Die C | D-2240 | | | | | | |
| | TangoBlackPlus FullCure 980 | | 1,12-1,13 | | 0,8-1,5 | 170-220 | | 2,4 | 26-28 | | | | | | |
| | TangoPlus FullCure 930 | | 1,12-1,13 | | 0,8-1,5 | 170-220 | | 2,4 | 26-28 | | | | | | |
| | TangoBlack FullCure 970 | | 1,12-1,14 | | 1,8-2,4 | 45-55 | | 3,5 | 35-40 | | | | | | |
| TangoGray FullCure 950 | | 1,16-1,17 | | 3-5 | 45-55 | | 8-12 | 73-77 | | | | | | | |
| MATERIALI BICOMPONENTE (DIGITALI) | | | | | | | | | | | | | | | |
| | RIGIDI | | carico a rottura oy (Mpa) | all. a rottura %e (%) | modulo flex. (Gpa) | res.Flex. (Mpa) | res.impatto Izod KIC (J / m) | Shore D | Rockwell M | T. Distors. @0,45Mpa (°C) | T. Distors. @1,82Mpa (°C) | Rammollin Tg (°C) | assorbimento (%) | | |
| | densità p (g / cm3) | modulo elastico E (Gpa) | | | | | | | | | | | | D-792 | D-638-03 |
| TRASPARENTI | FullCure720 + TangoBlack: | | | | | | | | | | | | | | |
| | DM 7210 | | - | 2,2-2,5 | 50-55 | 15-25 | 2,3-2,7 | 80-90 | - | - | 45-50 | - | - | - | |
| | DM 7220 | | - | 2,0-2,3 | 50-55 | 10-25 | 2,2-2,6 | 75-85 | - | - | 45-50 | - | - | - | |
| OPACHI | FullCure720 + VeroBlack: | | | | | | | | | | | | | | |
| | DM DOTS 7513 | | - | 2,0-3,0 | 50-65 | 15-25 | 2,7-3,3 | 80-110 | 20-30 | - | 45-50 | - | - | - | |
| | DM GRID 7523 | | - | 2,0-3,0 | 50-65 | 15-25 | 2,7-3,3 | 80-110 | 20-30 | - | 45-50 | - | - | - | |
| RIGIDI | VeroBlues + VeroBlack: | | | | | | | | | | | | | | |
| | DM 8210 | | - | 2,0-3,0 | 50-60 | 15-25 | 1,9-2,5 | 60-70 | 20-30 | - | 45-50 | - | - | - | |
| | VeroWhitePlus + VeroBlack: | | | | | | | | | | | | | | |
| | DM 8310 | | - | 2,0-3,0 | 50-65 | 10-25 | 2,2-3,2 | 75-110 | 20-30 | - | 45-50 | - | - | - | |
| | DM 8320 | | - | 2,0-3,0 | 50-65 | 10-25 | 2,2-3,2 | 75-110 | 20-30 | - | 45-50 | - | - | - | |
| | DM 8330 | | - | 2,0-3,0 | 50-65 | 10-25 | 2,2-3,2 | 75-110 | 20-30 | - | 45-50 | - | - | - | |
| | VeroWhitePlus + TangoPlus: | | | | | | | | | | | | | | |
| | DM 8425 | | - | 1,4-2 | 35-45 | 20-30 | 1,4-1,8 | 45-60 | 25-35 | - | 40-43 | - | - | - | |
| | VeroWhitePlus + TangoBlackPlus: | | | | | | | | | | | | | | |
| | DM 8505 Grey20 | | - | 1,7-2,3 | 40-60 | 15-25 | 1,5-2,5 | 55-75 | 22-35 | - | 40-45 | - | - | - | |
| POLIPROPILENE | DurusWhite + VeroWhitePlus/VeroBlue/VeroBlack/FullCure720: | | | | | | | | | | | | | | |
| | DM 4310 | | - | 1,2-1,6 | 30-40 | 40-50 | 1,3-1,7 | 40-50 | 35-45 | - | 40-45 | - | - | - | |
| | DM 4410 | | - | 1,2-1,6 | 30-40 | 40-50 | 1,3-1,7 | 40-50 | 35-45 | - | 40-45 | - | - | - | |
| | DM 4510 | | - | 1,2-1,6 | 30-40 | 40-50 | 1,3-1,7 | 40-50 | 35-45 | - | 40-45 | - | - | - | |
| | DM 4710 | | - | 1,2-1,6 | 30-40 | 40-50 | 1,3-1,7 | 40-50 | 35-45 | - | 40-45 | - | - | - | |
| | VeroWhitePlus + TangoPlus: | | | | | | | | | | | | | | |
| | DM 8430 | | - | 1,1-1,7 | 29-38 | 25-35 | 1,2-1,5 | 35-45 | 21-40 | - | 38-41 | - | - | - | |
| | VeroWhitePlus + TangoBlackPlus: | | | | | | | | | | | | | | |
| | DM 8530 Grey60 | | - | 1,1-1,7 | 29-38 | 25-35 | 1,2-1,5 | 35-45 | 21-40 | - | 38-41 | - | - | - | |
| | ABS | RGD515 + RGD535: | | | | | | | | | | | | | |
| RGD5160-DM Digital Abs-like | | - | 2,6-3,0 | 55-60 | 25-40 | 1,7-2,2 | 65-75 | 65-80 | 85-87 | 67-69 | 55-68 | 51-55 | 47-53 | | |
| RGD5160-DM Abs-like CURED | | - | 2,6-3,0 | 55-60 | 25-40 | 1,7-2,2 | 65-75 | 65-80 | 85-87 | 67-69 | 55-68 | 51-55 | 47-53 | | |
| SIMILGOMMA | SIMILGOMMA | | densità p (g / cm3) | | carico a rottura oy (Mpa) | all. a rottura %e (%) | | res.Strappo (N / mm) | Shore A | | | | | | |
| | | | D-792 | | D-412 | D-412 | | D-624 Die C | D-2240 | | | | | | |
| | TangoBlack + VeroWhitePlus/VeroBlue/VeroBlack/FullCure720: | | | | | | | | | | | | | | |
| | DM 9110 | | - | 2,0-4,0 | 45-55 | | | 7-9 | 75-85 | | | | | | |
| | DM 9120 | | - | 3,0-5,0 | 35-45 | | | 13-17 | 80-90 | | | | | | |
| | DM 9130 | | - | 7,0-11,0 | 35-45 | | | 45-50 | 90-100 | | | | | | |
| | DM 9210 | | - | 2,0-4,0 | 45-55 | | | 7-9 | 75-85 | | | | | | |
| | DM 9220 | | - | 3,0-5,0 | 35-45 | | | 13-17 | 80-90 | | | | | | |
| | DM 9230 | | - | 7,0-11,0 | 35-45 | | | 45-50 | 90-100 | | | | | | |
| | DM 9310 | | - | 2,0-4,0 | 45-55 | | | 7-9 | 75-85 | | | | | | |
| | DM 9320 | | - | 3,0-5,0 | 35-45 | | | 13-17 | 80-90 | | | | | | |
| | DM 9330 | | - | 7,0-11,0 | 35-45 | | | 45-50 | 90-100 | | | | | | |
| | DM 9410 | | - | 1,3-1,17 | 110-139 | | | 5,5-7,14 | 35-49 | | | | | | |
| | DM 9420 | | - | 1,3-1,18 | 110-140 | | | 5,5-7,15 | 35-50 | | | | | | |
| | DM 9430 | | - | 1,3-1,19 | 110-141 | | | 5,5-7,16 | 35-51 | | | | | | |
| | TangoGray + TangoBlack: | | | | | | | | | | | | | | |
| | DM 9510 | | - | 1,3-1,20 | 110-142 | | | 5,5-7,17 | 35-52 | | | | | | |
| | TangoGray + VeroBlack: | | | | | | | | | | | | | | |
| | DM 9610 | | - | 1,3-1,21 | 110-143 | | | 5,5-7,18 | 35-53 | | | | | | |
| | TangoBlackPlus/TangoPlus + VeroWhitePlus: | | | | | | | | | | | | | | |
| | DM 9740 | | - | 1,3-1,8 | 110-130 | | | 5,5-7,5 | 35-40 | | | | | | |
| | DM 9750 | | - | 1,9-3,0 | 95-110 | | | 7,5-9,5 | 45-50 | | | | | | |
| | DM 9760 | | - | 2,5-4,0 | 75-85 | | | 11-13 | 57-63 | | | | | | |
| | DM 9770 | | - | 3,5-5,0 | 65-80 | | | 15,5-17,5 | 68-72 | | | | | | |
| | DM 9785 | | - | 5,0-7,0 | 55-65 | | | 23-25 | 80-85 | | | | | | |
| | DM 9795 | | - | 8,5-10,0 | 35-45 | | | 41-44 | 92-95 | | | | | | |
| | DM 9840 | | - | 1,3-1,8 | 110-130 | | | 5,5-7,5 | 35-40 | | | | | | |
| | DM 9850 | | - | 1,9-3,0 | 95-110 | | | 7,5-9,5 | 45-50 | | | | | | |
| | DM 9860 | | - | 2,5-4,0 | 75-85 | | | 11-13 | 57-63 | | | | | | |
| | DM 9870 | | - | 3,5-5,0 | 65-80 | | | 15,5-17,5 | 68-72 | | | | | | |
| DM 9885 | | - | 5,0-7,0 | 55-65 | | | 23-25 | 80-85 | | | | | | | |
| DM 9895 | | - | 8,5-10 | 35-45 | | | 41-44 | 92-95 | | | | | | | |